

KDCOAT WR HARDENER

Technical Data Sheet

Description

Clear liquid.

Available in 1 litre units.

Use

Hardener for KDCOAT photoemulsions for improved water resistance. Screens treated with KDCOAT WR HARDENER can be reclaimed, but it is necessary to use a high pressure water spray.

Application

- Expose and develop as normal. Correct exposure is still recommended for maximum durability.
- Dry stencil.
- Treat with KDCOAT WR HARDENER on both sides of the dry stencil with a soft brush.
- Remove excess hardener from fine detailed areas with an air line or by blotting.
- Dry for a minimum of 10 minutes at 40-60°C.

Shelf Life/Storage

2 years, if stored at room temperature.

Prevent from freezing.

In the interest of health and safety always wear appropriate protective clothing.

Read Safety Data Sheet for full protection information.